

GOLD SYNTHETIC SUPER MAT PAINT



Application Recommendations

Application Areas

- Can be used safely with appropriate undercoat with on wood, iron-steel, cement, concrete, plaster, interior and exterior surfaces.

Equipment



Synthetic Anticorrosion



Synthetic Undercoat



Gold Synthetic Super Mat Paint

Equipment



Scraper



Gypsum trowel



Puttyshovel



Spatula



Trowel



Dust Cloth



Brush



Mixer



Adjustable Stick




Paint Bucket

Surface Preparation



Mortar




Concrete



Cement Board



Gypsum Panels



Old Plastic Paint



Plaster Board



Glasstextile



Wallpaper

• Application surfaces must be removed from oil, dirt, rust and bliste red paint.

• Should be made absolutely sanders before old painted wall and wooden surfaces before application, surfaces must be cleaned and priming with Gold synthetic super matt paint .Old Painted and metal surface must be free from rust with sandpaper.If not signs of rust surface should be priming with synthetic undercoat and should then be painted with Gold synthetic super matt paint Topcoat after correction surface with fine sandpaper.

• New wood surfaces to be painted surfaces must be primed with Gold synthetic super matt paint after saturating the wood preservative.Should be applied twice Gold Antirust new painted and iron-steel surfaces.

• Gold synthetic super matt paint Topcoat by brush, roller, or spray application to bring consistency must be thoroughly mixed with the

synthetic thinner thinned 5-10%.


• Gold synthetic super matt paint Topcoat applied sanded prepa red surfaces after 24 hours by brush, roller, or spray gun. Must be waited 1 day between layer application.

• Airless spray pressure of 120-140 bar, nozzle angle 50 °, size should be 0.013 inches.

• Tools should be cleaned with thinner immediately after use.

• Temperature should be between 5 ° C-30 ° C during the appli cation.

Application



During application and during the subsequent 24 hours at the ambient temperature of the surface should be +5 ° C.



Before application Gold synthetic super matt paint Paint should be mixed.



Gold synthetic super matt paint thinned with clean water 10% and application for two layer by brush, roller or spray.



Should be waited minimum 6 hours between layers.

After Application

Application tools should be washed with water after use immediately.

GOLD SYNTHETIC SUPER MAT PAINT



Exterior

Interior

Solvent

Product Description

- ◆ Modified alkyd resin based topcoat glossy synthetic paint.

Application Areas

- ◆ Can be used safely with appropriate undercoat with on wood, iron-steel, cement, concrete, plaster, cement board, gypsum board, OSB, MDF interior and exterior surfaces.

Advantages

- ◆ It has superior cover power.
- ◆ It has a stylish look with semi-mat features.
- ◆ Excellent cleanable and has adhesion to a substrate.



Bright



Brush



Roll



Spray Pistole

Technical specifications:

Structure

- ◆ Alkyd resin based, Solvent based

Diluting

- ◆ Solvent

Appearance on the packing

- ◆ Dark, Stable, Jelly

Dry Appearance

- ◆ Matt, Pastel, Smooth

Color

- ◆ White and 32 colors in the colour chart

Water. Vaporpermeability

- ◆ SD (m) (TS EN ISO 7783-2): Approximately: 50

Drying Time

- ◆ (between +5 +35 °C)
Touching time: 3 hours Doesn't hold dust for 8 hours. Complete drying time: 24 hours. Lower temperature or high relative humidity lengthens the drying time.

Coverage

- ◆ Depending on the surface smoothness and absorbency approximately 10-12 m²/lt. per a layer.

Shelf Life

- ◆ In package and in 5-35 °C 2 years

Packing

- ◆ 20 - 3 kg tin bucket.

Safety Recommendations

- ◆ S2: Keep out the reach of children.
- ◆ S24/25: Avoid contact with eyes and skin.
- ◆ S26: In case of contact with eyes immediately wash with water and contact with a doctor.
- ◆ S28: In case of contact with skin immediately wash with water.
- ◆ S29: Do not discharge into drains or water courses.
- ◆ S46: If swallowed, seek medical advice immediately and show the container or label. Mix before using. Close the cover after using. Protect from frost and direct sunlight.



Quality Certificate

- ◆ TSE TS 5808
Public exposure No. 04.524/604.506/E3